

# Corning® SMF-28® Ultra Optical Fiber

## Product Information



Corning® SMF-28® Ultra optical fiber is an ITU-T Recommendation G.652.D compliant optical fiber with Corning’s enhanced low-loss and bend fiber technologies. This full-spectrum fiber has bend performance that exceeds the ITU-T Recommendation G.657.A1 standard and still splices the same as the installed base of standard single-mode fibers such as SMF-28e+ fiber. SMF-28 Ultra fiber offers industry-leading specifications for attenuation, macrobend loss, and polarization mode dispersion values, which provide a solid foundation for new network deployments as well as upgrades to existing networks. Since Corning brought the first fiber to market more than 40 years ago, Corning’s leadership in single-mode fiber innovation has been unparalleled.

### Optical Specifications

#### Maximum Attenuation

Wavelength (nm)	Maximum Value* (dB/km)
1310	≤ 0.32
1383**	≤ 0.32
1490	≤ 0.21
1550	≤ 0.18
1625	≤ 0.20

\* Alternate attenuation offerings available upon request.

\*\* Attenuation values at this wavelength represent post-hydrogen aging performance.

#### Attenuation vs. Wavelength

Range (nm)	Ref. $\lambda$ (nm)	Max. $\alpha$ Difference (dB/km)
1285 – 1330	1310	0.03
1525 – 1575	1550	0.02

The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength ( $\lambda$ ) by more than the value  $\alpha$ .

#### Macrobend Loss

Mandrel Radius (mm)	Number of Turns	Wavelength (nm)	Induced Attenuation* (dB)
10	1	1550	≤ 0.50
10	1	1625	≤ 1.5
15	10	1550	≤ 0.05
15	10	1625	≤ 0.30
25	100	1310, 1550, 1625	≤ 0.01

\*The induced attenuation due to fiber wrapped around a mandrel of a specified radius.

#### Point Discontinuity

Wavelength (nm)	Point Discontinuity (dB)
1310	≤ 0.05
1550	≤ 0.05

#### Cable Cutoff Wavelength ( $\lambda_{cc}$ )

$\lambda_{cc} \leq 1260$  nm

#### Mode-Field Diameter

Wavelength (nm)	MFD ( $\mu$ m)
1310	9.2 ± 0.4
1550	10.4 ± 0.5

#### Dispersion

Wavelength (nm)	Dispersion Value [ps/(nm·km)]
1550	≤ 18.0
1625	≤ 22.0

Zero Dispersion Wavelength ( $\lambda_0$ ): 1304 nm ≤  $\lambda_0$  ≤ 1324 nm

Zero Dispersion Slope ( $S_0$ ):  $S_0 \leq 0.092$  ps/(nm<sup>2</sup>·km)

#### Polarization Mode Dispersion (PMD)

	Value (ps/√km)
PMD Link Design Value	≤ 0.04*
Maximum Individual Fiber PMD	≤ 0.1

\*Complies with IEC 60794-3: 2001, Section 5.5, Method 1, (m = 20, Q = 0.01%), September 2001.

The PMD link design value is a term used to describe the PMD of concatenated lengths of fiber (also known as PMD<sub>0</sub>). This value represents a statistical upper limit for total link PMD. Individual PMD values may change when fiber is cabled.

#### How to Order

Contact your sales representative, or call the Optical Fiber Customer Service Department:  
Ph: 1-607-248-2000 (U.S. and Canada)  
+44-1244-525-320 (Europe)

Email: [cofic@corning.com](mailto:cofic@corning.com)  
Please specify the fiber type, attenuation, and quantity when ordering.



## Dimensional Specifications

Glass Geometry		Coating Geometry	
Fiber Curl	≥ 4.0 m radius of curvature	Coating Diameter	242 ± 5 μm
Cladding Diameter	125.0 ± 0.7 μm	Coating-Cladding Concentricity	< 12 μm
Core-Clad Concentricity	≤ 0.5 μm		
Cladding Non-Circularity	≤ 0.7%		

## Environmental Specifications

Environmental Test	Test Condition	Induced Attenuation
		1310 nm, 1550 nm, and 1625 nm (dB/km)
Temperature Dependence	-60°C to +85°C*	≤ 0.05
Temperature Humidity Cycling	-10°C to +85°C up to 98% RH	≤ 0.05
Water Immersion	23°C ± 2°C	≤ 0.05
Heat Aging	85°C ± 2°C	≤ 0.05
Damp Heat	85°C at 85% RH	≤ 0.05

\*Reference temperature = +23°C

Operating Temperature Range: -60°C to +85°C

## Mechanical Specifications

### Proof Test

The entire fiber length is subjected to a tensile stress ≥ 100 kpsi (0.69 GPa).\*

\*Higher proof test levels available.

### Length

Fiber lengths available up to 63.0 km/spool.

## Performance Characterizations

Characterized parameters are typical values.

Core Diameter	8.2 μm
Numerical Aperture	0.14 NA is measured at the one percent power level of a one-dimensional far-field scan at 1310 nm.
Effective Group Index of Refraction ( $N_{eff}$ )	1310 nm: 1.4676 1550 nm: 1.4682
Fatigue Resistance Parameter ( $N_d$ )	20
Coating Strip Force	Dry: 0.6 lbs. (3N) Wet, 14-day room temperature: 0.6 lbs. (3N)
Rayleigh Backscatter Coefficient (for 1 ns Pulse Width)	1310 nm: -77 dB 1550 nm: -82 dB